## PATENT NO. 349459 METHOD FOR COATING NANO-MAGNETIC PARTICLES WITH PHARMACOLOGICALLY ACTIVE SUBSTANCE

## APPLICATION NO. 2855/MUM/2012

APPLICANT

Bhavnagar University, Gujarat, India

### ABSTRACT

The present invention provides a method for coating the nanomagnetic particles using anaesthetic drug comprising the steps (i) synthesizing nano sized magnetite magnetic particles using chemical coprecipitation technique; (ii) aqueous based slurry of the said particles are further used for coating procedure; (iii) wet magnetite particles are mixed with lignocaine hydrochloride molecules in presence of carbodiimide; the above mixture is kept in rotary shaker for uniform shaking at room temperature for 3 to 5 hrs; after shaking, the coated nanomagnetic particles are washed several times with water to get rid of unreacted and/or free drug molecules.

#### **INVENTOR**

Desai, Rucha, Pradipkumar

Department of Nanoscience & Technology, PD Patel Institute of Applied Sciences, Charotar University of Science & Technology, Charusat Campus, Changa, Gujarat

Davariya, Vipul, Savjibhai Thanapipli, Dist. Unagadh, Ta. Vanthli, Gujarat

Upadhyay, Ramesh, Venkataramaiah Principal, PD Patel Institute of Applied Sciences, Charotar University of Science & Technology, Charusat Campus, Changa, Gujarat

Mehta, Rasbindu, Virprasad 10, Nilmani Tenament, Gogha Circle, Bhavnagar, Gujarat

# CLAIM 1

A method for coating the nanomagnetic particles using anaesthetic drug Lignocaine comprising the steps 5 (i) synthesizing nano sized magnetite magnetic particles using chemical coprecipitation technique; (ii) aqueous based slurry of the said particles are further used for coating procedure; (iii) wet magnetite particles are mixed with lignocaine hydrochloride 10 molecules in presence of carbodiimide; the above mixture is kept in rotary shaker for uniform shaking at room temperature for 3 to 5 hrs; (iv) after shaking, the coated nanomagnetic particles are washed several times with water to get rid of unreacted and/or free drug molecules.